

**THE CLAIMS**

What is claimed is:

1. A method of alkylating an aliphatic or aromatic hydrocarbon with an  
5 olefin, which comprises contacting the aliphatic or aromatic hydrocarbon with the olefin in  
the presence of a solid polymeric onium polyhydrogen fluoride complex under conditions  
sufficient for the alkylation of the aliphatic or aromatic hydrocarbon.
2. The method of claim 1, wherein the aliphatic ~~or aromatic~~ BHO  
10 hydrocarbon is a C<sub>4</sub>-C<sub>10</sub> saturated, branched hydrocarbon.
3. The method of claim 2, wherein the olefin is a C<sub>2</sub>-C<sub>8</sub> ~~alkene~~ 8 BHO.
4. The method of claim 3, wherein the alkylation of the aliphatic ~~or aromatic~~ HND BHO  
15 ~~aromatic~~ hydrocarbon produces a high-octane C<sub>6</sub>-C<sub>12</sub> branched alkane.
5. The method of claim 3, wherein the molar ratio of the saturated,  
branched hydrocarbon to the olefin ranges from about 2:1 to about 20:1.
6. The method of claim 1, wherein the ~~aliphatic or~~ aromatic HND BHO  
20 hydrocarbon is a C<sub>6</sub>-C<sub>20</sub> aromatic hydrocarbon.
7. The method of claim 6, wherein the olefin is a C<sub>2</sub>-C<sub>20</sub> alkene.
8. The method of claim 7, wherein the alkylation of the ~~aliphatic or~~ HND BHO  
25 aromatic hydrocarbon produces a detergent alkylate.
9. The method of claim 8, wherein the detergent alkylate is further  
sulfonated under conditions sufficient to produce a detergent.
- 30 10. The method of claim 1, wherein the solid polymeric onium  
polyhydrogen fluoride complex comprises a polymeric material containing in some or all of

its repeat units a nitrogen, phosphorus, or sulfur atom capable of forming an onium fluoride moiety upon reaction or complexation with anhydrous hydrogen fluoride.

11. The method of claim 1, wherein the solid polymeric onium  
5 polyhydrogen fluoride complex is poly(vinylpyridinium) polyhydrogen fluoride or poly(aminomethyl)styryl polyhydrogen fluoride.

12. The method of claim 1, wherein the polymeric onium polyhydrogen  
fluoride component comprises from about 70 to about 95 weight percent hydrogen fluoride.  
10

13. The method of claim 1, which further comprises contacting the  
aliphatic or aromatic hydrocarbon with the olefin in the presence of a Lewis acid halide or a  
strong Bronstead acid.

14. The method of claim 13, wherein the Lewis acid halide or strong  
15 Bronstead acid is present in an amount from about 0.1 to about 10 weight percent of the  
solid polymeric onium polyhydrogen fluoride complex.

15. A process for forming a solid polymeric onium polyhydrogen  
20 fluoride complex, which comprises contacting a homopolymer or copolymer including, in at  
least one repeat unit, a nitrogen, phosphorus, or sulfur atom, capable of forming an onium  
fluoride moiety upon reaction or complexation with a source of hydrogen fluoride under  
conditions sufficient to form the solid polymeric onium polyhydrogen fluoride complex.

16. A solid polymeric onium polyhydrogen fluoride complex formed by  
25 the process of claim 15 that is capable of facilitating alkylation of an aliphatic or aromatic  
hydrocarbon with an olefin.

17. The process of claim <sup>15</sup>~~16~~, wherein the source of hydrogen fluoride is  
30 ~~an alkylation product.~~ *anhydrous hydrogen fluoride*

18. A process for removing hydrogen fluoride from an alkylation  
product, which comprises contacting the alkylation product with a homopolymer or

copolymer including, in at least one repeat unit, a nitrogen, phosphorus, or sulfur atom, capable of forming an onium fluoride moiety upon reaction or complexation with a source of hydrogen fluoride, under conditions sufficient for the homopolymer or copolymer to complex hydrogen fluoride.

5

19. The process of claim 18, wherein the removal of hydrogen fluoride occurs in the absence of any aqueous or caustic treatment.

10 20. A method of regenerating a solid polymeric onium polyhydrogen fluoride complex useful as an alkylation catalyst, which process comprises contacting the solid polymeric onium polyhydrogen fluoride complex made by the process of claim 15 with a source of hydrogen fluoride under conditions sufficient to regenerate the solid polymeric onium polyhydrogen fluoride complex.

15

21. The method of claim 20, wherein the source of hydrogen fluoride is ~~an alkylation product.~~ *anhydrous hydrogen fluoride*

*6/10*